#### WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



### INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5: A61C 8/00, A61F 2/02

**A1** 

(11) International Publication Number:

WO 92/05745

(43) International Publication Date:

16 April 1992 (16.04.92)

(21) International Application Number:

PCT/SE91/00672

(22) International Filing Date:

4 October 1991 (04.10.91)

(30) Priority data:

9003206-1

A61L 27/00

8 October 1990 (08.10.90)

SE

(71) Applicant (for all designated States except US): AKTIEBO-LAGET ASTRA [SE/SE]; S-151 85 Södertälje (SE).

(75) Inventor/Applicant (for US only): HANSSON, Stig, Gustav, Wilhelm [SE/SE]; Gåsmossen 32, S-436 00 Askim (SE).

(74) Agents: DANIELSSON, Sten et al.; AB Astra, Patent Department, S-151 85 Södertälje (SE).

(81) Designated States: AT, AT (European patent), AU, BB, BE (European patent), BF (OAPI patent), BG, BJ (OAPI patent), BR, CA, CF (OAPI patent), CG (OAPI patent), CH, CH (European patent), CI (OAPI patent), CM (OAPI patent), CS, DE, DE (European patent), DK, DK (European patent), ES, ES (European patent), FI, FR (European patent), GA (OAPI patent), GB, GB (European patent), CN (OAPI patent), GB, GB (European patent) ropean patent), GA (OAPI patent), GB, GB (European patent), GN (OAPI patent), GR (European patent), HU, IT (European patent), JP, KP, KR, LK, LU, LU (European patent), MC, MG, ML (OAPI patent), MR (OAPI patent), MN, NL, NL (European patent), NO, PL, RO, SD, SE, SE (European patent), SN (OAPI patent), SU<sup>+</sup>,TD (OAPI patent), TG (OAPI patent), US.

Published

With international search report.

(54) Title: METHOD FOR THE PREPARATION OF IMPLANTS MADE OF TITANIUM OR ALLOYS THEREOF

#### (57) Abstract

The invention relates to a method for treating the surface of surgical implants made of titanium or a titanium alloy, for instance dental implants, for implanting in bone tissue, in which method a rough surface is obtained. At the same time a cleaning action is obtained, should there be any contaminations. The method is characterized in that the surface is blasted with particles of an oxide of titanium, preferably titanium dioxide. In this way an implant having an improved retension in bone tissue is obtained.

+ See back of page

BNSDOCID: <WO 9205745A1 1 >

### + DESIGNATIONS OF "SU"

Any designation of "SU" has effect in the Russian Federation. It is not yet known whether any such designation has effect in other States of the former Soviet Union.

	FC	OR THE PU	URPOSES OF INFORMATION O	NLY	•
	<i>:</i>				·
	Codes used to identify St	ates party	to the PCT on the front pages	of pamphl	ets publishing internation
appli	cations under the PCT.				
ΑT	Austria	ES	Spain	MG	Madagascar
AU	Australia	Fl	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	ltaly	RO	Romania
CF	Central African Republic	JP	Japan	SD	Sudan
CC	Congo	KP ·	Democratic People's Republic	SE	Sweden
CH	Switzerland		of Korea	SN	Senegal
CI	Côte d'Ivoire	KR	Republic of Korea	su+	Soviet Union
CM	Cameroon	Ll	Licchtenstein	TD	Chad
CS	Czechoslovakia	LK	Sri Lanka	TG	Togo
DE	Germany	LU	Luxembourg	us	United States of America
DK	Denmark	MC	Monaco		

METHOD FOR THE PREPARATION OF IMPLANTS MADE OF TITANIUM OR ALLOYS THEREOF.

## Technical field of the invention

5 The present invention relates to a method for treating the surface of surgical implants, particularly dental implants, made of c.p. titanium or of a titanium alloy and intended to be implanted in bone tissue. One object of the invention is to achieve an implant having an improved 10 retention in bone tissue by providing the implant with an improved surface structure. An additional object of the invention is to achieve an implant having a great degree of purity in regard of contaminating substances which may endanger the retention of the implant in the bone tissue. 15 The invention is described below in connection with dental implants, but the invention can be adapted to the surface treatment of other surgical implants to be implanted in bone tissue.

# Background to the invention

The most sensitive part in a dental implant system is the fixture, i. e. that part of the system which is screwed or inserted into a hole in the jaw bone and which thus comes into direct contact with the tissues in the jaw. A suitable material for these implants is titanium. The use thereof as a material in surgical implants was suggested early (for instance by Leventhal et al in the Journal of Bone and Joint Surgery vol 33A, No 2, April 1951).

It is known that the fixture has to be very clean if the ingrowth of the bone tissue onto the implant, the so called osseointegration process, shall function in an optimal way. It even has been maintained that a contamination corresponding to a monomolecular layer could endanger the continued existence of the implant in the tissue.

## SUBSTITUTE SHEET

35

20

The structure of the surface of the implant also is importants:

Luco matte

10

The Swedish patent SE-C-416175 (7902035-0) for instance states that a better result of an implant operation is achieved if an implant with a surface of titanium oxide is provided with pores having a size of 10 - 1000 nm defined as being "micropits". This patent specification does however not clearly show how this surface differs from other known surfaces, for instance turned surfaces, or to what extent the retention of the implant is improved.

Several other publications have discussed the importance of the surface roughness for the retention of the implant, for instance the academic treatise by Jan Lundskog: "Heat and Bone Tissue" Laboratory of Experimental Biology, Department of Anatomy, University of Gothenburg, Sweden 1972, the article "Adhesion of bone to titanium", by S.G. Steinemann, J. Eulenberger, P.-A. Maeusli and A.

- Schroeder in Biological and Biomechanical Performance of Biomaterials, edited by P. Christel, A. Meunier and A.J.C. Lee, Elsevier Science Publishers B.V., Amsterdam 1986 and the article "Removal Torques for Polished and Rough Titanium Implants", Carlsson L., Röstlund T., Albrektsson
- 25 B., Albrektsson T., Int J Oral Maxillofac Implants, 1988; 3:21-24. These publications indicate that it may be better with an implant surface having larger (macroscopic) irregularities or pores than those described in the above Swedish patent.

30

35

Implants have been made by cutting operations for a long time, primarily by turning. According to the above Swedish patent such a machining may result in a surface with microscopic irregularities. Several cleaning methods have been suggested and used, such as cleaning with organic solvents, electropolishing, sand blasting and treatment with alkalic and acid solutions.

One commonly used cleaning method thus is blasting with well known blasting agents, such as sand or aluminium oxide. Blasting with a blasting material having correctly sized particles results in the surface roughness which is desired in order to obtain a good mechanical retention in the bone. One problem with blasting the surface of the fixture is however that, although the existing contaminations may be removed, residues from the blasting agent may remain on the surface of the implant. The blasting agents commonly used, for instance aluminium oxide, thus may result in contaminations that are impossible or very difficult to remove in a subsequent cleaning process.

#### 15 Description of the invention.

The object of the invention is to provide a treatment of implants made of titanium or titanium alloys which in one operation both ensures that the surface of the implant is clean and that the surface has the macroscopic structure which is necessary for a good retention of the implant in the jaw bone.

According to the present invention this is achieved in
that implants of titanium or of an alloy of titanium are
blasted with particles of an oxide of titanium, preferably
titanium dioxide. Since titanium exposed to air has a
chemically resistant layer of oxide, the most important
one being titanium dioxide, the blasting operation will
not introduce any foreign, contaminating material onto the
implant surface, although effectively removing existing
contaminations and providing the desired roughness.

In accordance with a preferred embodiment of the invention the oxide used for the the blasting comprises titanium dioxide.

BNSDOCID: <WO\_\_\_\_\_9205745A1\_I\_>

20

- Mara further preferred embodiment of the invention, the solution oxide, which preferably comprises titanium dioxide, comprises particles having a grain size within the range of 1 - 2000 μm, more preferably particles having a grain size within the range of 1 - 300 μm. In another preferred embodiment the particles have a grain size within the range of 1 - 50 μm. Particles having a size being close to the upper limit preferably are used in the treatment of larger orthopaedic prostheses.

10

It has proved that the fixture obtains a surprisingly good force-transmitting capacity in implants whose surface have been treated in accordance with the invention. This is important since the fixture is subjected to considerable forces which are to be transmitted to the bone. The 15 fixture therefore has to have a design which allows a safe transmission of these forces to the bone. As indicated above, the strength of the bond between the bone and the implant is improved if the surface of the fixture has a 20 macroscopic roughness which is superimposed on the geometrical design of the fixture. The use of blasting particles having a size of 1 - 50 µm results for instance in a size of the irregularities on the surface of the implant in the range 1 - 25 μm (the size of the irregularities are normally smaller than the size of the 25 particles). Smaller irregularities may of course also be superimposed on these irregularities. In this range of the size of the roughness, the strength of the bond implant bone is considerably improved. It has been shown that this strength-improving effect is reduced if the size is 30 · reduced.

The strength-improving effect is negligible at sizes below 0.3 µm. Larger irregularities, 5 - 200 µm, result in an additional improvement of the strength of the bond implant - bone, but irregularities in the size range 100 - 200 µm may in some cases interfere negatively with the geometrical design of the implant. The size of the

irregularities here can be defined as an approximative diameter or width of a rounded respectively an oblong shape.

#### 5 Examples

A. Fixtures made of titanium of the kind used by the applicant, AB Astra (Astra Meditec), were thoroughly cleaned and degreased in a conventional manner and were then blasted in a blasting equipment "Sandmaster, 10 Ultrafine Sandblaster Type FG3-82, Wülsag, Zofingen, Switzerland". A titanium dioxide powder having a grain size of 10 - 53 µm was used ("Metco 102", Metco Scandinavia AB, Vårby, Sweden, normally used for plasmaor flame-spraying). Air was used as carrying medium in the 15 blasting process. Each fixture was blasted about 20 seconds. The fixture was rotated and the blasting nozzle was moved up and down along the longitudinal axis of the fixture at an angle of about 90 degrees relative to the longitudinal axis of the fixture. The air pressure of the 20 apparatus was set at 1 Bar (100kPa) above atmospheric pressure.

Some of the blasted fixtures were examined in an electron microscope. A rough, irregular surface was observed. The size of the irregularities were about 5 - 15 µm with superimposed irregularities having a smaller size.

The implants were then washed in organic solvents and a number of fixtures were examined by means of ESCA (Electron Spectroscopy for Chemical Analysis) in order to study the degree of cleanliness. The implants proved to be exceptionally clean.

B. The above experiment was repeated with another blasting equipment, "Abrasive Blaster, Mark 3", delivered by Belle de St Claire, 16147 Valerio St, Van Nuys, California 91406, USA. Blasting agent and carrying medium were the

same as above. The air pressure of the apparatus was set at 80 psi (5,5 bar, 550 kPa). Again a dental implant fixture from Astra Meditec was blasted. The blasting nozzle was moved axially up and down the surface of the implant about 5 - 10 mm away from the the surface. The fixture was simultaneously rotated. The nozzle then was moved over the outer lower end of the fixture. Duration about 20 seconds. Visually the fixture displayed a dull surface after the blasting. During an examination under a microscope it proved that the blasting had resulted in a rough surface.

### Animal tests.

## 15 I. Histological analysis.

10 fixtures, which had been blasted in accordance with the above Example A, were operated into the upper jaw of Beagle dogs together with untreated control fixtures. A

20 histological analysis after 2 respectively 4 months showed that the blasted implants had been osseo-integrated in the same way as the untreated control fixtures.

II. Summary of results obtained in animal studies relating
to osseointegration and fixation strength of "smooth"
respectively blasted surface of titanium implants.

The geometrical design and the surface (macro-, micro-structure) of an implant are two factors considered important for the osseointegration. In order to study these factors and the differences in the degree of the osseointegration and the strength of the fixation two studies comprising threaded and cylindrical implants having smooth alternatively blasted surfaces were made.

35

30

#### Study 1.

The study comprised 3 dogs (labrador) which each had 6
threaded fixtures implanted (i.e. 18 in all). Of these 18
fixtures 9 had a conventional structure of the surface
whereas the remaining 9 fixtures had been treated with a
blasting method in accordance with the above Example A.

- After a healing period of 1 respectively 6 months for both implant surfaces a torque test was performed in which the fixtures were screwed out and the torque which was necessary for this was registered with a torque meter.
- 15 The results were that the fixtures having conventional surfaces could be removed when torques in the range of 35 45 Ncm were applied. The fixtures which had been blasted could not be removed although a torque of 100 Ncm was applied. The testing equipment broke at torques exceeding 100 Ncm.

#### Study 2.

In this animal study both cylindrical and threaded
fixtures having alternatively conventional surfaces and
surfaces blasted according to the Example were compared in
accordance with the following schedule:

	Cylindrical	implant,	conventional	surface	:	6	fixtures
30	11	**	blasted	**	:	6	11
	Threaded	11 -	conventional	11	:	6	11
	11	11	blasted	***	:	6	ti

The 24 fixtures were implanted in 6 dogs, 4 in each, in accordance with a random schedule.

The result was that all the fixtures having a conventional surface could be removed at torques ranging from 30 to 40

BNSDOCID: <WO\_\_\_\_\_9205745A1\_I\_>

Ncm. The blasted implants, both the threaded and the cylindrical ones, could however not be removed despite the application of torques of 100 Ncm. The equipment could not stand higher torques.

5 .

The conclusion is that the blasted surface gives a considerably higher strength in the bond titanium - bone.

As mentioned in the introduction, it should be understood
that the present invention only has been illustrated by
means of dental implants and that the method according to
the invention of course is applicable to all kinds of bone
implants having a surface to be implanted made of titanium
or titanium alloys.

15

It further should be pointed out that, although the invention has been illustrated using air blasting, airless (mechanical) blasting and wet blasting also can be used.

10

#### CLAIMS.

- Method for treating the surface of implants of titanium or an alloy of titanium, characterized in that the surface is blasted with particles of a titanium oxide.
  - 2. Method according to claim 1, c h a r a c t e r i z e d in that the oxide is titanium dioxide.
- 3. Method according to claim 1 or 2, character ized in that the particles used have a size within the range of 1 to 2000 µm.
- 4. Method according to claim 3, c h a r a c t e r i z e d in that the particles used have a size within the range of 1 to 300  $\mu m$ .
- 5. Method according to claim 3, c h a r a c t e r i z e d in that the particles used have a size within the range of 1 to 50  $\mu$ m.
- 6. Method according to any one of the preceding claims,c h a r a c t e r i z e d in that the implant treated is25 a dental implant.
  - 7. Implant, c h a r a c t e r i z e d in that it has been treated according to any one of claims 1 6.
- 8. Method for treating toothlessness, c h a r a c t e r i z e d in that a dental implant is treated in accordance with any one of claims 1 - 6, in that one or several implants whose surface have been so treated is implanted into the jaw of a patient in need of such a treatment, whereafter one or several teeth or dental bridges are attached to the implant(s).

9. Method for increasing the fixation strength off orthopaedic implants characterized in that the surface of the implants is blasted with a titanium oxide in accordance with any one of claims 1 - 5.

BNSDOCID: <WO\_\_\_\_ 9205745A1 | >

# INTERNATIONAL SEARCH REPORT

International Application No PCT/SE 91/00672

International Application No. PC17 3C 317 00072								
1. CERSSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) 6								
According to international Patent Classification (IPC) or to both National Classification and IPC IPC5: A 61 C 8/00, A 61 F 2/02, A 61 L 27/00								
II. FIELD	S SEARCHED							
II. FIELDS SEARCHED  Minimum Documentation Searched 7								
Classificat	Classification System Classification Symbols							
IPC5	A	61 C; A 61 F; A 61 L						
	Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in Fields Searched <sup>8</sup>							
SE,DK,	FI,NO cla	sses as above						
III. DOCL	MENTS CONS	IDERED TO BE RELEVANT®						
Category *	Citation	of Document, <sup>11</sup> with indication, where ap	propriate, of the relevant passages 12	Relevant to Claim No.13				
A	8 De	16175 (P I BRÅNEMARK ET cember 1980, the whole document 	AL)	1-7,9				
A	16 J	62565 (PERMELEC ELECTRO uly 1990, the whole document	DE LTD)	1-7,9				
** Special categories of cited documents: 10  "A" document defining the general state of the art which is not considered to be of particular relevance  "E" earlier document but published on or after the international filing date  "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)  "O" document referring to an oral disclosure, use, exhibition or other means  "P" document published prior to the international filing date but in the priority date claimed  IV. CERTIFICATION  "T" later document published after the international filing or priority date and not in conflict with the application cited to understand the principle or theory underlying cited to understand the principle or theory underlying document of particular relevance, the claimed invention and involve an inventive atep where the priority date document is combined with one or more other such document is combined with one or more other such document such combination being obvious to a parson sin the art.  "A" document of particular relevance, the claimed invention or cannot be considered to involve an inventive step where the priority date and not in conflict with the application cited to understand the principle or theory underlying cite				e, the claimed invention annot be considered to e, the claimed invention an invention the or more other such docu-				
Date of the Actual Completion of the International Search  Date of Mailing of this International Search Report								
9th January 1992 1992 -01- 15								
Internation	International Searching Authority  Signature of Authorized Officer  Jack Headlen d'							
SWEDISH PATENT OFFICE //Jack Hedlund orm PCT/ISA/210 (second sheet) (January 1985)								

BNSDOCID: <WO\_\_\_\_\_9205745A1\_I\_>

FURTH	R INFORMATION CONTINUED FROM THE SECOND SHEET	Company of the state of the sta
., "	LASSOTT CONTRACTOR	N. 1984
	The state of the s	
	·	
	·	11 13
		.1
		30
	1	1
	BSERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE 1	
This intern	national search report has not been established in respect of certain claims under Article 17(2) (a)	for the following reasons:
1. [X] Cla	im numbers, because they relate to subject matter not required to be searched by this Aut	hority, namely:
Se	ee PCT Rule 39.1(iv): Methods for treatment of t	- h -
חנ	iman or animal body by surgery or therapy as we	11
as	s diagnostic methods.	
2. Ciz	im numbers, because they relate to parts of the international application that do not compl utrements to such an extent that no meaningful international search can be carried out, specificall	y with the prescribed
		·
	· · · · · · · · · · · · · · · · · · ·	1
3. Cla	im numbers because they are dependent claims and are not drafted in accordance with the	second and third sen-
VI. 🗌 01	SSERVATIONS WHERE UNITY OF INVENTION IS LACKING 2	
This Into	emational Searching Authority found multiple inventions in this international application as follows	ı:
	·	
		İ
	·	
1. 🗀 🚑	all required additional search fees were timely paid by the applicant, this international search repo lms of the international application.	ort covers all searchable
2. As onl	only some of the required additional search fees were timely paid by the applicant, this internation y those claims of the international application for which fees were paid, specifically claims:	nal search report covers
3. No	required additional search fees were timely paid by the applicant. Consequently, this international to the invention first mentioned in the the claims. It is covered by claim numbers:	search report is restrict-
. [] ^-	all geometric claims could be accorded without -15-15 to 15-15	
4. ☐ dia	all searchable claims could be searched without effort justifying an additional fee, the internationa not invite payment of any additional fee.	I Searching Authority
Remark o	on Protest	
🔲 тье	additional search fees were accompanied by applicant's protest.	
□ Но	protest accompanied the payment of additional seach fees.	
DOT'		

\_BNSDOCID: <WO\_\_\_\_\_9205745A1\_I\_>

## ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO.PCT/SE 91/00672

This annex tists the patent family members relating to the patent documents cited in the space-mentioned international search report. The members are as contained in the Swedish Patent Office EDP file on 31/10/91

The Swedish Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report		Publication date	Patent family member(s)		Publication date	
SE-B-	416175	80-12-08	BE-A- CA-A- CH-A-B- DE-A-C- FR-A-B- GB-A-B- JP-A- LU-A- NL-A- SE-A- US-A-	881953 1157694 653245 3007446 2450599 2045083 55120864 82222 8001241 7902035 4330891	80-06-16 83-11-29 85-12-31 80-09-18 80-10-03 80-10-29 80-09-17 80-06-06 80-09-09 80-09-08 82-05-25	
SE-B-	462565	90-07-16	DE-A-C- FR-A- GB-A-B- JP-C- JP-A- US-A-	3639607 2591529 2183256 1575861 62120403 5034186	87-05-27 87-06-19 87-06-03 90-08-24 87-06-01 91-07-23	